


JAM 70

Product description

- IR cut film
- Application : Automotive, Architecture
- Features :
 - UV light cut off 99%
 - Excellent performance of IR cut off
 - Controlled reflectance and transmittance

Strong structure:



Typical properties

Items	Code	EPS 7090	Test method
Visible light transmittance	VLT	67.39	ISO 9050
Visible light reflectance	RV	11.94	ISO 9050
Ultraviolet rejection	UVR	>99.9	LS-182
Infrared rejection	IRR	91.2	LS-182
Solar energy transmittance	TE	39.48	ISO 9050
Solar energy reflectance	RE	14.3	ISO 9050
Solar energy absorption	AE	46.22	ISO 9050
Solar heat gain coefficient	SHGC	0.5448	JIS R3106
Shading coefficient	SC	0.63	JIS A5759
Total solar energy rejection	TSER	48.46	ISO 9050

*All of the data were evaluated by attaching a 1/8" glass in the UV/VIS spectrometer.